

Product: igumid® EG+ GLP

Mai 14. 2018

General Properties:

Density:	1,13 g/cm ³
Color:	Blue
Saturation with moisture absorption at 23°C / 50% r. h.:	< 0,1 -%
Saturation with water:	very low

Mechanical Properties: ¹⁾

Pull-flexural modulus:	1900 MPa
Shore D hardness:	73

Thermal Properties: ^{2), 3)}

Highest long term service temperature:	80°C
Lower short term application temperature:	100°C
Higher short term environment temperature: ²⁾	110°C
Lowest service temperature:	0°C

Electrical Properties:

Surface resistivity:	>10 ¹² Ω
----------------------	---------------------

¹⁾ Dependent of the application, in contact with other media, is an individual proof required

²⁾ Without additional load; no slip

³⁾ Relaxation not excluded

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.